

# TECHNICAL DATA SHEET

**ceratun**  
**S.SAB.425**

**CAS NUMBER** : 68476-25-5  
**EINECS NUMBER** : 2706667  
**MATERIAL CODE** : S.SAB.425 (KS.12.B.0005)  
**PRODUCTION PLANT** : Kaltun - Cine / AYDIN/ TURKIYE  
**SHORT DESCRIPTION OF MATERIAL** : **CERATUN S.SAB.425** is a high quality Sodium Feldspar, produced from deposits in the Cine-Milas region, Turkiye.

## PHYSICAL & CHEMICAL PROPERTIES OF MATERIAL:

	Particle Size Distribution				Others			
	Sieve Residue %				Humidity * %		Hardness	Density
	+10mm	+5mm	+0,5mm	-0,5mm	Summer	Winter	Mohs	g/cm <sup>3</sup>
<b>Typ.</b>	<b>0,0</b>	<b>5,0</b>	<b>57,0</b>	<b>43,0</b>	<b>3,0</b>	<b>5,0</b>	<b>6</b>	<b>2,60</b>
<b>Min.</b>	-	-	-	<b>35,0</b>	-	-	-	-
<b>Max.</b>	<b>1,0</b>	-	-	-	<b>5,0</b>	<b>7,0</b>	-	-

\* Summer season conditions are valid from the beginning of May till the end of September.

	Chemical Analysis **									
	SiO <sub>2</sub>	Al <sub>2</sub> O <sub>3</sub>	Fe <sub>2</sub> O <sub>3</sub>	TiO <sub>2</sub>	CaO	MgO	Na <sub>2</sub> O	K <sub>2</sub> O	P <sub>2</sub> O <sub>5</sub>	L.O.I
<b>Typ.</b>	<b>63,48</b>	<b>18,25</b>	<b>0,40</b>	<b>0,35</b>	<b>2,00</b>	<b>3,00</b>	<b>8,50</b>	<b>0,56</b>	<b>0,21</b>	<b>3,25</b>
<b>Min.</b>	-	<b>17,25</b>	-	-	-	<b>2,50</b>	<b>8,00</b>	-	-	-
<b>Max.</b>	<b>65,00</b>	-	<b>0,45</b>	<b>0,40</b>	-	<b>3,50</b>	-	-	-	-

\*\*With XRF Spectrometer

The above figures are typical, average values derived from numerous measurements. This is not a specification

**kaltun**

Aydin- Mugla Karayolu 35. Km. 09500 Cine/Aydin-TURKIYE

Phone : +90 256 729 16 00

Fax : +90 256 729 16 15

Web : <http://www.kaltun.com>

e-mail : [kaltun@kaltun.com.tr](mailto:kaltun@kaltun.com.tr)

Doc.No : Cera006  
Issued Date : 13.05.2014  
Revision : 2